

香港粉嶺安居街33號

香港粉嶺安全街29A號

## 佳力高試驗中心有限公司 CASTCO TESTING CENTRE LTD.

33, On Kui Street, Fanling, Hong Kong.

Tel: 2677 2138

E-mail: castco@netvigator.com Website: www.castco.com.hk

29A, On Chuen Street, Fanling, Hong Kong.

Fax: 2677 0351





Determination of skid resistance value for clay and calcium silicate pavers (BS6677: Part 1: 1986 Appendix E)

Date of issue: 29 August 2015

Page 1A of 1 page (s)

Castco LRN: HC0150724-1

## Details as supplied by client

Client: Top Excel (Hong Kong) Ltd.

Client's ref. no.: --

Contract no .: --

Job title: --

Sample type: Well's Anti Slip Treatment

Work size: 200 mm x 200 mm x 8 mm (L x W x T)

Date cast: --

Bulk sample size: --

## Laboratory Test Result

Date sample received: 24 July 2015

Date of test: 28 July 2015

Specimen no.	Wet skid resistance value	Mean wet skid resistance value
no.	1	
1	74	
2	74	
3	74	74
	, ,	
4	73	-
5	73	,

Remarks: 1. Test result relates only to the specimen tested.

2. This test report supersedes previous test report of Castco LRN: HC0150724-1 issued on 04 August 2015.

Checked by:

CHEUNG CHUN POXIG Assistant Technical Officer

End of Report

Approved Signatory:

**WONG KA MAN** Laboratory Manager

Form No. NI\_6677\_SRV\_T dd27/06/2002