

74 Kent Street Brooklyn, New York 11222-1517

E-mail: dllabs@aol.com

Phone (718) 383-5080

Fax (718) 383-7445

Independent Testing and Consulting Laboratory Serving the Coatings, Sealant, Waterproofing and Building Materials Industries Since 1932

October 5, 2010

Tagawa Sangyo Company, Ltd. 1924 Yugeta, Tagawa-shi, Fukuoka-ken, 826-0041 Japan

Attn: Mr. Nobuyoshi Yukihira

Re: DL-16215B

OBJECTIVE

To determine the hardness of test panels coated with a lime plaster coating material.

PRODUCT TESTED

The test panels were coated with a pre-mixed lime plaster material identified as:

Shikkui Sora (Shikkui Plaster)

PROCEDURE

The hardness was determined in accordance with the procedures outlined in:

ASTM D 2240 - Standard Test Method for Rubber Property – Durometer Hardness

TEST RESULTS

The **Shikkui Sora** pre-mixed lime plaster coating material exhibited the following hardness properties.

Shore A Durometer 95-97

Shore D Durometer 61-62

DL Labs, Inc.

Mario Lazaro, Jr.

Assistant Technical Director